

PRODUCT MANUAL

Product name:	Zinc Peroxide Nanoparticles coated with 2-(2-methoxyethoxy)acetate ligands
Product number:	ZnO ₂ -MEAA-S

Solution preparation (5 mg/mL)

- (1) Weigh out 10 mg of ZnO₂-MEAA-S powder and transfer to glass vial.
- (2) Add 2 mL of an appropriate solvent (i.e., DMSO, toluene, H₂O) to the vial.
- (3) Sonicate for at least 10 minutes.
- (4) Store the resulting colloidal solution at room temperature.
- (5) Solution should be stable for at least few days. If white precipitate appears at the bottom of the vial, sonicate for at least 10 minutes again.

Caution: Nanoparticles

Handling: Wear personal protective equipment, face and eyes protection. Wear protective gloves. Avoid contact with skin, eyes or clothing. Avoid ingestion and inhalation. Ensure proper ventilation. Avoid dust formation. Avoid breathing vapors, dust, mist or gas.

PRODUCT INTENDED FOR RESEARCH AND DEVELOPMENT PURPOSES ONLY